

CLAIMS

What is claimed is:

- 5 1. A method for chemical treatment of biological tissue, comprising the steps of:
- (a) providing a quantity of biological tissue which contains
 connective tissue protein; and,
- (b) contacting the biological tissue with a solution under oxidizing
 conditions for sufficient time to impart enhanced stability
 compared to traditional means of fixing connective tissue protein
10 within the biological tissue.
-
- 2: A method according to Claim 1 wherein the oxidizing conditions are provided in
 step (b) by heating the solution in the presence of oxygen.
3. A method according to Claim 2 wherein the presence of oxygen is provided by
 ambient oxygen in the solution.
4. A method according to Claim 2 wherein at least some of the oxygen present is
 provided by allowing the solution to contact atmospheric air, oxygen or an oxygen-
20 containing gas solution.
5. A method according to Claim 2 wherein at least some of the oxygen present is
 provided by bubbling oxygen or an oxygen-containing gas mixture through the solution.
- 25 6. A method according to Claim 1 wherein the oxidizing conditions are provided in
 step (b) by combining an oxidizing agent with the solution in the presence of oxygen.
7. A method according to Claim 6 wherein the oxidizing agent is selected from the
 group of oxidizing agents consisting of a peroxide, a compound containing peroxide,
30 hydrogen peroxide, a periodate, a compound containing periodate, sodium periodate, a

diisocyanate compound, a halogen, a compound containing halogen, n-bromosuccinimide, a permanganate, a compound containing permanganate, ozone, a compound containing ozone, chromic acid, sulfonyl chloride, a sulfoxide, a selenoxide, and combinations thereof.

5 8. A method according to Claim 6 wherein the presence of oxygen is provided by ambient oxygen in the solution.

9. A method according to Claim 6 wherein at least some of the oxygen present is provided by allowing the solution-oxidizing agent mixture to contact atmospheric air, oxygen or an oxygen-containing gas mixture.

10 10. A method according to Claim 6 wherein at least some of the oxygen present is provided by bubbling oxygen or an oxygen-containing gas mixture through the solution.

15 11. A method according to Claim 1 wherein the oxidizing conditions are provided in step (b) by irradiating the solution in the presence of oxygen.

20 12. A method according to Claim 11 wherein the solution is irradiated by a type of radiation energy selected from the group of alpha ionizing radiation, beta ionizing radiation, ultraviolet radiation, electron beam radiation, gamma rays, and combinations thereof.

25 13. A method according to Claim 11 wherein the presence of oxygen is provided by ambient oxygen in the solution.

14. A method according to Claim 11 wherein at least some of the oxygen present is provided by allowing the solution to contact atmospheric air, oxygen or an oxygen-containing gas mixture.

15. A method according to Claim 11 wherein at least some of the oxygen present is provided by bubbling oxygen or an oxygen-containing gas mixture through the solution.

16. A method according to Claim 1 wherein the solution is flowing.

17. A method according to Claim 16 wherein the flowing of the solution is effected by placing the solution and the tissue in a container, wherein the solution is heated and circulated through the container.

18. A method according to Claim 1, wherein step (b) comprises the steps of:
placing the tissue in a solution containing 0.2-2.0 % glutaraldehyde;
maintaining the glutaraldehyde solution at 25-70 °C for a period of
0.5-60 days; and,
removing the tissue from the glutaraldehyde solution.

19. A method according to Claim 18 wherein the solution has a glutaraldehyde concentration of about 0.625%.

20. A method according to Claim 19 wherein the 0.625% glutaraldehyde solution is maintained at about 45-55 °C for a period of between about 7 and 14 days.

21. A method according to Claim 1 wherein the solution is a fixative.

22. A method according to Claim 21 wherein fixative is glutaraldehyde.

23. A method according to Claim 21 wherein fixative is Denacol.

24. A method according to Claim 1 wherein the solution is peroxide.

09915489-072601
T09270-68451660

25. A bioprosthesis comprising tissue that has been prepared by a method comprising the steps of:

(a) providing a quantity of biological tissue which contains connective tissue protein; and,

(b) contacting the biological tissue with a solution under oxidizing conditions for sufficient time to result in crosslinking of connective tissue protein within the biological tissue.

26. A bioprosthesis according to Claim 25 wherein the oxidizing conditions in step (b) are provided by heating the solution in the presence of oxygen.

27. A bioprosthesis according to Claim 25 wherein the presence of oxygen in step (b) is provided by ambient oxygen in the solution.

28. A bioprosthesis according to Claim 25 wherein at least some of the oxygen present is provided by allowing the solution to contact atmospheric air, oxygen or an oxygen-containing gas solution.

29. A bioprosthesis according to Claim 25 wherein at least some of the oxygen present in step (b) is provided by bubbling oxygen or an oxygen-containing gas mixture through the solution.

30. A bioprosthesis according to Claim 25 wherein the oxidizing conditions are provided in step (b) by combining an oxidizing agent with the solution in the presence of oxygen.

31. A bioprosthesis according to Claim 30 wherein the oxidizing agent is selected from the group of oxidizing agents consisting of a peroxide, a compound containing peroxide, hydrogen peroxide, a periodate, a compound containing periodate, sodium periodate, a diisocyanate compound, a halogen, a compound containing halogen, n-

bromosuccinimide, a permanganate, a compound containing permanganate, ozone, a compound containing ozone, chromic acid, sulfuryl chloride, a sulfoxide, a selenoxide, and combinations thereof.

5 32. A bioprosthesis according to Claim 30 wherein the presence of oxygen is provided by ambient oxygen in the solution-oxidizing agent mixture.

 33. A bioprosthesis according to Claim 30 wherein at least some of the oxygen present is provided by allowing the solution-oxidizing agent mixture to contact atmospheric
10 air, oxygen or an oxygen-containing gas mixture.

 34. A bioprosthesis according to Claim 30 wherein at least some of the oxygen present is provided by bubbling oxygen or an oxygen-containing gas mixture through the
15 solution.

 35. A bioprosthesis according to Claim 25 wherein the oxidizing conditions are provided in step (b) by irradiating the solution in the presence of oxygen.

 36. A bioprosthesis according to Claim 35 wherein the solution is irradiated by a
20 type of radiation energy selected from the group consisting of: alpha ionizing radiation, beta ionizing radiation, ultraviolet radiation, electron beam radiation, gamma rays, and combinations thereof.

 37. A bioprosthesis according to Claim 35 wherein the presence of oxygen is
25 provided by ambient oxygen in the solution.

 38. A bioprosthesis according to Claim 35 wherein at least some of the oxygen present is provided by allowing the solution to contact atmospheric air, oxygen or an oxygen-
30 containing gas mixture.

39. A bioprosthesis according to Claim 35 wherein at least some of the oxygen present is provided by bubbling oxygen or an oxygen-containing gas mixture through the solution.

5 40. A bioprosthesis according to Claim 25 wherein the solution is flowing.

41. A bioprosthesis according to Claim 40 wherein the flowing of the solution is effected by placing the solution and the tissue in a fixation container, wherein the solution is heated and circulated through the container.

10

091548-02601
T09270-63451660